

TEST REPORT

(Electronic version)



No:200169468

VERIFICATION WEBSITE: www.gttc.net.cn

VERIFICATION CODE: CBVC-0325-54

ISSUE DATE:2020-06-13

扫码下载报告



APPLICANT: SUZHOU DORO NEW MATERIAL TECHNOLOGY CO., LTD
ADDRESS: FENGHUANG SCIENCE &TECHNOLOGY VENTURE PARK 3F, FENGHUANG TOWN ,ZHANGJIAGANG CITY

INFORMATION CONFIRMED BY APPLICANT:

25GSM MELTBLOWN

QUANTITY: 1 PACK

DATE RECEIVED/DATE TEST STARTED: 2020-06-11

CONCLUSION:

BACTERIAL FILTRATION EFFICIENCY

M

NOTE: "M" -MEET THE STANDARD'S REQUIREMENT "F" -FAIL TO MEET THE STANDARD'S REQUIREMENT
"---" -NO COMMENT

REMARK:

TEST MATERIAL, TESTED AND JUDGED BY YY/T 0969-2013 AS PER CLIENT'S REQUIREMENT.

THIS REPORT IS THE ENGLISH TRANSLATION VERSION OF THE REPORT 200121074.


ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION).

COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.

THE EXPERIMENT WAS CARRIED OUT AT No.1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.

APPROVED BY:

WanLi Hu ENGINEER



PAGE 1 OF 2

TEST REPORT

(Electronic version)

No:200169468

BACTERIAL FILTRATION EFFICIENCY (%)

(YY 0469-2011 ANNEX B, TEST BACTERIA: STAPHYLOCOCCUS AUREUS ATCC 6538, TEST AREA: 49cm², FLOW RATE: 28.3L/min, MEAN PARTICLE SIZE: 3.0 μm, RESULT OF THE POSITIVE CONTROL: 1.9×10³ CFU, RESULT OF THE NEGATIVE CONTROL: <1CFU)

		REQUIREMENT
BFE ₁	99.5	≥95
BFE ₂	99.3	(YY/T 0969-2013)
BFE ₃	99.2	



————End of Report————

PAGE 2 OF 2